

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Harmony Timber Floors
96 Kortum Drive
Burleigh QLD 4220

Test Number : 22-003047
Issue Date : 17/08/2022
Print Date : 17/08/2022

Sample Description Clients Ref : "Harmony Whitewashed SPC Hybrid Vinyl flooring"
SPC Hybrid Vinyl flooring
End Use : Flooring
Nominal Composition : Vinyl top/Stone core/ EVA rubber underlay
Nominal Mass per Unit Area/Density : Approx: 12kg/m2
Nominal Thickness : 6.5mm



275452

59849

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Harmony Timber Floors
96 Kortum Drive
Burleigh QLD 4220

Test Number : 22-003047
Issue Date : 17/08/2022
Print Date : 17/08/2022

AS 4586-2013 Appendix A

Slip Resistance Classification of new Pedestrian Surface Materials Wet Pendulum Test Method

Date of Testing	17/08/2022					
Test Temperature (20±5degC)	21 °C					
Sample Preparation	Sample washed with pH neutral detergent and dried					
Test Direction	Length					
Fixed/Unfixed	Unfixed					
Slider No 96 Batch No	97					
Length	1	2	3	4	5	SRV
British Pendulum Number	37	38	36	37	38	37
Classification	P3					

Equipment: Cooper Pendulum Skid Tester Serial No: 1433-01 Calibrated 21/09/2021
Slider prepared using P400 and 3µm lapping film.

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance and wear on their slip resistance be checked.

275452

59849

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR